

Drossbach Technical Data Sheet For Flexible Convuluted Tubing / Conduit



Data Sheet	TD-008 "NP" Nylon		
Revision:	10	Date:	09/27/17
Base Material:	Nylon		
Material Code:	NP		

Our commitment to quality is our commitment to success

Product Description

Flexible convuluted tubing / conduit manufactured from a nylon 6 co-polymer, impact modified resin.

Performance Enhancers

Flame Retardant	Yes (see UL Notes below "Not yet Certified")
UV Inhibitor	No
Heat Stabilizer	Yes

Performance Characteristics

Flexibility	Good
Abrasion Resistance	Excellent
Chemical Resistance	Good See Chemical Resistance Report: CR-008
Continuous Operating Temperature	-40 to +125C (-40 to +257F) Min. 3000 Hrs.
Short Term" Operating temperatures	-40 to +149C (-40 to +300F) Max. 168 Hrs

Typical Physical Properties	Test Method	Value	Units
Specific Gravity/Density	ASTM D792	1.07	-
Elongation @ Break	ASTM D638	>100	%
Elongation @ Yield	ASTM D638	7	%
Tensile Strength @ 25C	ASTM D638	34	MPa
2% Secant Modulus	-	-	-
Flexural Modulus	ASTM D790	610	MPa
Melting Point	ASTM D3418	428 (220)	°F (°C)
Notched Izod Impact Test	ASTM D256	640	J/m
Heat Deflection Temperature @66psi	ASTM D648	317 (158.5)	°F (°C)
Heat Deflection Temperature @264psi	ASTM D648	117 (47)	°F (°C)

Material Certifications

Delphi / Packard	M-2170
Ford	-
General Motors	GMP.PA6.003, GM 7001-M PA6
Chrysler	MS DB41 CPN 2785
ASTM	D4066 PA260
Underwriters Laboratory	Meets the test requirements UL-94 HB @ 1.5 mm (Not UL certified)
FMVSS 302	Max. Burn rate of 101.2mm / min. (1.0 mm thick)
Other	This product has been tested and will meet the requirements of UL 94 HB. This product has not been certified yet By UL but Documentation is available showing test results complying to the UL test.

Notes

- (1) Drossbach does not claim or state any UV life or warranty unless stated above in the "Other" section", as we do not have any control over its end use environment.
- (2) All "UL" and FMVSS 302 flame ratings are for the resin used to manufacture our product, not for our end product. The ratings are created by testing standard "UL" and "FMVSS" plaque specimens, not tubing samples.
- (3) Compliant with the European Union's **Directive 2002/95/EU (RoHS)**, **REACH Directive** and the **Conflict Minerals Initiative**.
- (4) Only product designated as **UL 94 "V0"** in the Material Certification section above can be certified as **non-Halogenated product**.
- (5) If a product is designated as flame retardant but has no material certification listed, this product is a Drossbach internally blended material blended with a flame retardant additive. It is tested to an internal flame test (DR-006) that holds no claimed warranty.



Drossbach N.A. Inc.
 PO Box 2000
 157 N. Murray St.
 Trenton, Ontario Canada
 K8V 6G7
 Phone: (613) 394-4817 Fax: (613) 394-5516

Web Site Address: <http://www.drossbach.com>

Email: info@drossbachllc.com

An ISO/TS 16949 and ISO-9001

Registered Company



Drossbach LLC
 1500 Commerce Drive
 Stow, OH, 44224 USA
 Phone: (330) 688-8460
 Toll Free: (800) 841-5804
 Fax: (330) 688-8465